



TK-FLOOR HARDENER & DENSIFIER 5329

Item No. TK-5329

PRODUCT DESCRIPTION

TK-FLOOR HARDENER & DENSIFIER 5329 is a colorless, odorless blend of 100% active sodium silicate and silicate to strengthen, harden, densify and dustproof new or existing concrete and masonry floors. It penetrates into the concrete, sealing the pores and capillaries and creating a chemical reaction within the concrete to produce a hard mineral film that is resistant to water, chemicals and abrasion.

Features:

- Increases the strength of the surface by filling the pores - decreasing porosity while increasing density.
- Treated surfaces have higher resistance against water, chemicals and abrasion and require less maintenance and up-keep.
- Creates a breathable surface for passage of moisture vapor.
- Contains no solvents or fumes, is non-toxic, non-combustible and complies with all VOC regulations.
- Does not leave a film and will not make surfaces slippery.
- Short downtime; floors can be put back into service immediately after application.
- Compatible with floor and carpeting adhesives and most stripping paints.

USES:

Suitable for interior use on concrete floors and surfaces in industrial, warehousing, manufacturing and food service environments. Its odorless formulation makes it ideal for enclosed, inhabited areas where solvent-containing systems may be hazardous to use.

APPLICATION PROCEDURES

PREPARATION:

The surface must be clean and free of dirt, oil, curing compounds or foreign materials. Patch all cracks and remove any laitance. Any cleaners must be thoroughly rinsed off and allowed to dry. Although the surface may be damp at the time of application, it must not contain standing water as this will dilute TK-FLOOR HARDENER & DENSIFIER 5329 and will negatively affect its performance.

New Concrete Preparation - New concrete must be allowed a minimum of 7 days curing before applying this product. Recommended methods of curing are via water curing or by covering the surface with poly. Curing may be accomplished using TK-DC WB DISSIPATING CURING COMPOUND 2519*, however application instructions must be followed precisely to ensure complete removal of the curing resin.

APPLICATION:

TK-FLOOR HARDENER & DENSIFIER 5329 may be applied by sprayer, roller or brush. Work the product into the surface using a soft bristle brush or scrub pad. To increase the effectiveness of the product, use a mechanical scrubber. Continue working until the product begins to gel or

TECHNICAL DATA

V.O.C. Content:	0 g/L
A.I.M. Category:	Sealers Maximum VOC 400 g/l
Applicable Standards:	USDA authorization for use in meat and poultry processing plants.

TESTING DATA

	Test Method	Results
Impact Resistance:	ASTM C42	Increases resistance
Abrasion Resistance:	ASTM C779	33% increase in resistance
Hardening:	ASTM C39	42% increase in compressive strength at 7 days. 39% increase at 28 days over untreated samples.
Coefficient of Friction:	ASTM C1028	0.69 wet / 0.86 dry
Bonding Adhesion:	ASTM D3359	16.7% increase in epoxy adhesion. No change in polyurethane adhesion.
Light Exposure:	ASTM G23	No effect by ultra violet light or water spray exposure.

become slippery, then re-wet the surface and work for another 10-15 minutes. As the surface gels or becomes slippery again, flush with water and squeegee the surface dry. Finally, wait 30 minutes, then flush the surface once more with fresh water and squeegee dry.

APPLICATION NOTE: In order for the proper reaction to occur, the surface must remain saturated for a minimum of 30 minutes. Very porous or open concrete surfaces may result in faster drying. If this occurs, you must apply additional TK-FLOOR HARDENER & DENSIFIER 5329 to the surface and leave on for the full 30 minutes.

COVERAGE:

Surface	Coverage
Steel troweled concrete:	200 sq.ft./gal
Other concrete surfaces:	200 - 250 sq.ft./gal

Coverage rates are provided as a guideline only. Many factors including surface texture, porosity and weather conditions will determine actual coverage rates.

LIMITATIONS:

- Do not apply when ambient or substrate temperatures are below 32°F.
- Product may freeze but must be allowed to thaw completely before use.
- Over-application may cause discoloration or a white haze to develop.
- Brush out all puddles to prevent formulation of white residue.
- Protect surrounding metal, glass, wood, brick and painted surfaces.

PROTECTION OF VEGETATION, GLASS AND ALUMINUM SURFACES:

Avoid contact with live vegetation, glass and aluminum. If properly protecting these surfaces is impractical, the following steps should be performed:

- 1) Minimize contact of TK-FLOOR HARDENER & DENSIFIER 5329 with live vegetation, glass and aluminum surfaces.
- 2) If TK-FLOOR HARDENER & DENSIFIER 5329 comes into contact with glass or aluminum, thoroughly clean surfaces with Windex® or an ammonia cleaner while the material is still wet.

MAINTENANCE:

Use normal dust mopping or sweeping between occasional detergent and water cleansings.

FIRST AID:

- Consult this product's safety data sheet for additional health and safety information. Safety Data Sheets are available through TK distributors, the TK office and the TK website.

AVAILABILITY:

TK-FLOOR HARDENER & DENSIFIER 5329 is available through TK Distributors. Contact TK Products for the nearest distributor.

Packaged in 55-gallon drums, 5-gallon pails and 1-gallon cans.

FOR PROFESSIONAL USE ONLY

NOTES:

*TK-DC WB DISSIPATING CURING COMPOUND 2519 must be purchased separately

12/15 Last Rev. 04/15

CONDITIONS OF SALE/ LIMITED WARRANTY

TK Products, division of the Sierra Corporation, warrants that its products conform to the label descriptions, are free from manufacturing defects, and are fit for the ordinary purposes for which such goods are used. Inasmuch as the use of TK Products' product by others and other factors affecting product performance are beyond TK Products' control, TK Products does not guarantee the results to be obtained. There are no warranties except as stated herein, either express or implied, including implied warranties of merchantability or fitness for a particular purpose. SHOULD ANY TK PRODUCTS' PRODUCT FAIL TO GIVE SATISFACTORY RESULTS, TK PRODUCTS WILL REPLACE THE PRODUCT, OR AT ITS OPTION, REFUND THE PURCHASE PRICE. THIS IS THE SOLE AND EXCLUSIVE REMEDY FOR ANY FAILURE OF TK PRODUCTS' PRODUCTS TO PERFORM AS WARRANTED AND SHALL ALSO CONSTITUTE LIQUIDATED DAMAGES IN CASE OF LOSS. UNDER NO CIRCUMSTANCES SHALL THE BUYER BE ENTITLED TO ANY OTHER REMEDY OR DAMAGES. REMEDIES FOR INCIDENTAL AND CONSEQUENTIAL DAMAGES ARE SPECIFICALLY EXCLUDED. TK Products does not authorize any person to assume for it any other liability in connection with the sale or use of its products unless specifically authorized by TK Products in writing.

TK DISCLAIMER:

Every effort has been made to ensure the accuracy of the above information and to avoid infringement of any patent or copyright. The information is based on field tests by government and private agencies, as well as lab tests, and on technical data from raw material manufacturers. The person(s) specifying or requesting the use of these products is responsible for assuring their suitability for a specific use, as well as the proper application of the products. Where there is any question as to the suitability of a particular product, a small test patch is recommended. See also CONDITIONS OF SALE/ LIMITED WARRANTY (Section 7) above.



TK Products Construction Coatings

11400 West 47th Street Minnetonka, MN 55343
800-441-2129 toll free | 952-938-8084 fax | www.tkproducts.com